

NOTES — STANDARD SYSTEM BUILD-UP (TYPICAL) · SPECIFICATION SECTION 09 67 23 RESINOUS FLOORING

- 1. Substrate: Concrete mechanically prepared to CSP 3–5 (ICRI 310.2R), clean, sound, and dry.
- 2. Heavy-duty (HD) decorative flake system: urethane cement overlay, flake broadcast to rejection, two clear seal coats; the second coat within 24 hours of the first (per MavTop UF-HD System Guide).
- 3. Urethane cement is self-priming; no epoxy primer is installed under the slurry body.
- 4. Thicknesses per the referenced Maverick data sheet / system guide and the component product data sheets. Drawing not to scale.

MAVTOP UF-HD

STANDARD SYSTEM BUILD-UP · ISOMETRIC, EXPLODED
DWG MAV-TOP-UF-HD-001 · REV 2 · 10-10-2026
SUPERSEDES MAV-CRETE-UF-HD-001



MAVSEAL UPA
2nd Seal Coat, Applied Within 24 Hours · 6–8 mils

MAVSEAL UPA
1st Seal Coat · 12–16 mils

MAVTOP UF-HD
Pigmented Urethane Cement with Decorative Chip Broadcast to Rejection · 3/16 in. (1/4 in. after broadcast)

CONCRETE SUBSTRATE
Mechanically Prepared

Dept. ENGINEERING	Technical reference MavTop UF-HD System Guide	Created by MAVERICK	Approved by		
 25911 Northline Commerce Drive, Suite 306, Taylor, MI 48180 maverickperformancesolutions.com · sales@mavtechsol.com		Document type SYSTEM BUILD-UP · SCALE: NTS	Document status SHOP DRAWING		
		Title MavTop UF-HD	DWG No. MAV-TOP-UF-HD-001		
			Rev. 2	Date of issue 10-10-2026	Sheet 1/1